

OFFICE OF NAVAL RESEARCH

CONTRACT N00014-94-1-0101

R&T CODE 31321075

Technical Report #28

POLYSILANE-POLY(FERROCENYLSILANE) RANDOM COPOLYMERS.

by

K. Matyjaszewski, E. Fossum, R. Rulkens, I. Manners

Published

in the

Macromolecules, 28, 401 (1995)

Carnegie Mellon University
Department of Chemistry
4400 Fifth Avenue
Pittsburgh, PA 15213

June 30, 1995

Reproduction in whole or in part is permitted for any purpose of the United States Government

This document has been approved for public release and sale;
its distribution is unlimited.



DTIC QUALITY INSPECTED 5

19950630 194

REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE June 30, 1995		3. REPORT TYPE AND DATES COVERED Technical Report #28	
4. TITLE AND SUBTITLE Polysilane-Poly(ferrocenylsilane) Random Copolymers.				5. FUNDING NUMBERS N00014-94-1-0101	
6. AUTHOR(S) K. Matyjaszewski, E. Fossum, R. Rulken, I. Manners					
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Carnegie Mellon University Department of Chemistry 4400 Fifth Avenue Pittsburgh, PA 15213				8. PERFORMING ORGANIZATION REPORT NUMBER N00014-94-1-0101	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) Department of Navy Office of Naval Research 800 North Quincy Street Arlington, VA 22217-5000				10. SPONSORING/MONITORING AGENCY REPORT NUMBER Technical Report #28	
11. SUPPLEMENTARY NOTES					
12a. DISTRIBUTION/AVAILABILITY STATEMENT				12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) Thermal polymn. of ferrocenyldimethylsilane with tetramethyltetraphenyltetracyclosilane was carried out at various ratios of the comonomers. The exact compn. of copolymers depends on the initial ratio of monomers. All copolymers are segmental with alternating oligo(ferrocenylsilane) and oligosilane blocks.					
14. SUBJECT TERMS				15. NUMBER OF PAGES	
				16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT		18. SECURITY CLASSIFICATION OF THIS PAGE		19. SECURITY CLASSIFICATION OF ABSTRACT	
				20. LIMITATION OF ABSTRACT	

Polysilane - Poly(ferrocenylsilane) Random Copolymers

Eric Fossum and Krzysztof Matyjaszewski*

*Department of Chemistry, Carnegie-Mellon University
4400 Fifth Avenue, Pittsburgh, Pennsylvania 15213, USA.*


Ron Rulkens and Ian Manners*

*Department of Chemistry, University of Toronto
80 St. George St., Toronto, Ontario, Canada.*

Polymers based on inorganic elements continue to attract considerable interest because of their unique physical and chemical properties.¹ Polysilanes $[\text{SiR}_2]_n$ represent a novel class of these materials which exhibit σ -delocalization, photosensitivity, and thermochromic behaviour.^{1,2} Such characteristics have led to potential applications as photoconductors and photoresists. In addition, these polymers have also attracted attention as ceramic precursors.² Polysilanes have been prepared via a variety of methods including Wurtz² and dehydrogenative³ coupling, anionic polymerization of masked disilenes,⁴ and recently by ring-opening polymerization (ROP).^{5,6} In 1992 the synthesis of high molecular weight poly(ferrocenylsilanes) via the thermal ROP of silicon-bridged [1]ferrocenophanes was described.⁷ These macromolecules possess a main chain of alternating ferrocene and organosilane units and exhibit a range of interesting properties as a result of the presence of transition metals in the polymer backbone.⁸ The synthesis of copolymers of polysilanes and poly(ferrocenylsilanes) offers the possibility of tuning physical characteristics and of providing access to materials with unusual combinations of properties.⁹ In this communication we report on our attempts to thermally copolymerize cyclic silanes and silicon-bridged [1]ferrocenophanes.

The [1]ferrocenophane **1** polymerizes thermally at elevated temperatures in the melt to yield the poly(ferrocenylsilane) **2**. In addition, the anionic ROP of **3** in solution has been previously reported.⁵

We have now found that **3** also polymerizes thermally at 150°C to quantitatively yield poly(methylphenylsilane) **4**. Indeed, when the ROP of **3** was monitored by Differential Scanning Calorimetry (DSC), a large broad exotherm at 150°C was detected with an onset temperature of 90°C. Integration revealed the strain energy to be ca. 56 kJmol⁻¹, which is less than that determined for **1** (ca. 80 kJmol⁻¹) by similar methods.⁷



Thermal copolymerization experiments involving mixtures of **1** and **3** were carried out in various ratios (Table 1) and were performed in sealed, evacuated Pyrex tubes at 150 °C for 2 h. Under these conditions the reaction mixture transformed from a red melt into an immobile amber colored glass. Analysis of **5a** - **5c** by ¹H NMR (in C₆D₆) confirmed that no unreacted monomer **1** or **3** remained. The polymeric products **5a** - **5c** were isolated as pale amber powders by precipitation from THF into hexanes and possessed number average molecular weights (*M_n*) of 67,000 - 89,000.

Evidence that **5a** - **5c** are true copolymers rather than blends of the two homopolymers was provided by the use of Gel Permeation Chromatography (GPC) with an on-line photo diode array or detector, which allows for the simultaneous observation of multiple wavelengths. GPC traces for **5a** -

Subscription

By
Distribution/


Availability Codes

Dist

Avail and/or
Special

A-1

5c showed two absorptions at 330 nm and 450 nm which are close to those for poly(methylphenylsilane) and poly(ferrocenyldimethylsilane), respectively.^{2,10} The two traces overlapped exactly, which indicated that unless two homopolymers with identical molecular weights were present, the two different monomers were incorporated into a single copolymer. Photochemical degradation was found to be selective for the methylphenylsilane units, leaving the ferrocenylsilane segments intact. Thus, when photodegradation of 5 was carried out in THF using 340 nm UV light for 18 h, a GPC trace of the products showed no absorption at 330 nm indicating the absence of polysilane segments. In addition, the absorption at 450 nm for the ferrocenylsilane segments shifted to a shorter retention time (lower molecular weight) indicating that no high polymer remained. From the molecular weight of the degraded polymer it was possible to obtain the degree of polymerization of the ferrocenylsilane segments; in all cases this was relatively low (DP = 2 - 10) but an increase was detected as the amount of 1 in the initial monomer mixture was increased. The λ_{max} for the polysilane segments increased with an increasing proportion of 3 in the monomer mixture, ranging from 325 nm for 5a to 333 nm for 5c. These absorption values suggest that the polysilane segments are relatively short and do not approach the limit corresponding to $M_n = 3,000$ where the λ_{max} levels off at 338 nm.² This data indicated that 5a - 5c are copolymers which contain short segments of polysilane and poly(ferrocenylsilane).



5

Further structural characterization of 5a - 5c was provided by ^1H and ^{29}Si NMR spectroscopy. The ^1H NMR spectra of 5a - 5c (in C_6D_6) showed sharp signals for the ferrocenyldimethylsilane segments at 0.51 ppm (SiMe_2), and at 4.08 and 4.48 ppm ($\eta\text{-C}_5\text{H}_4$) and two broad signals for methylphenylsilane segments at -0.5 to 0.5 (Me) and 6.5 - 7.5 ppm (Ph).^{7,11} The integration ratio of the phenyl and cyclopentadienyl regions of the ^1H NMR spectra of 5 confirmed that the relative amounts of 2 and 4 in

the copolymers **5** were equal to the relative amounts of the two monomers **1** and **3** in the initial mixture prior to polymerization. Smaller, unresolved cyclopentadienyl resonances between 3.5 and 4.4 ppm were assigned to the ferrocenylsilane units near a juncture to a methylphenylsilane segment. Analysis of **5a** - **5c** by ^{29}Si NMR (in C_6D_6) showed resonances for ferrocenyldimethylsilane units at -6.4 ppm, a broad resonance for atactic methylphenylsilane segments from -37 to -40 ppm, and also revealed small peaks for SiMe_2 cross over groups between the ferrocenylsilane and methylphenylsilane segments at -6.6 and at -17.3 ppm.¹² The peaks are particularly apparent in the ^{29}Si NMR spectrum of polymer **5c** which possessed relatively short ferrocenylsilane blocks; in contrast, the resonances in the corresponding spectrum of **5a** are less intense as the ferrocenylsilane blocks are longer (Figure 1).

Cyclic voltammetric studies of **5a** - **5d** in CH_2Cl_2 showed the presence of two reversible oxidations at $E_{1/2} = 0.00$ V and at 0.23 V¹³ due to interacting iron atoms as found previously for poly(ferrocenylsilane) homopolymers.^{7,8} An irreversible oxidation with $E_p(\text{ox}) = 0.39$ V was also detected which corresponds to oxidation of the polysilane segments.¹⁴

In summary, the thermal ROP of mixtures of **1** and **3** provides a route to novel polysilane - poly(ferrocenylsilane) copolymers. It is interesting to note that these polymer structures are not available from the ROP of oligosilane-bridged $[n]$ ferrocenophanes ($n > 1$) as such species are insufficiently strained to polymerize.⁸ The exact composition of the copolymers was found to depend on the initial ratio of monomers **1** and **3**, but all are segmental in nature with alternating oligoferrocenylsilane and oligosilane blocks. Attempts to extend the scope of this type of copolymerization reaction are underway and we are also investigating the electronic and optical properties of the copolymers in detail.

Acknowledgements

The work at Carnegie-Mellon University was funded by the Office of Naval Research (ONR) and the National Science Foundation (NSF). The research at the University of Toronto was supported by the Institute of Chemical Science and Technology (ICST) and the Natural Science and Engineering Research Council of Canada (NSERC). In addition, IM is grateful to the Alfred P. Sloan Foundation for a Fellowship (1994-96).

References

1. (a) Mark, J.B.; Allcock, H.R.; West, R. *Inorganic Polymers*, Prentice Hall, 1992
(b) Allcock, H.R. *Adv. Mater.* 1994, 6, 106. (c) Manners, I. *J. Chem. Soc. Ann. Rep. Prog. Chem. (A)* 1992, 93. (d) *Inorganic and Organometallic Polymers*, edited by Allcock, H.R.; Wynne, K.; Wislan Neilson, P. ACS Symp. Ser. 572, Washington D.C. 1994.
2. Reviews: (a) West, R. *J. Organomet. Chem.* 1986, 300, 327 (b) Miller, R. D.; Michl, J. *Chem. Revs.* 1989, 89, 1359. (c) West, R. In *Chemistry of Organic Silicon Compounds*; Patai, S., Rappoport, Z., Eds.; Wiley: New York, 1989; p1207. (d) Matyjaszewski, K., *J. Inorg Organomet. Polym.* 1991, 1, 463.
3. (a) Aitken, C.; Harrod, J.F.; Samuel, E. *J. Organomet. Chem.* 1985, 279, C11.
(b) Aitken, C.; Harrod, J.F.; Samuel, E. *J. Am. Chem. Soc.* 1986, 108, 4059.
(c) Tilley, T.D. *Acc. Chem. Res.* 1993, 26, 22.
4. Sakamoto, K.; Obata, K.; Hirata, H.; Nakajima, M.; Sakurai, H. *J. Am. Chem. Soc.* 1989, 111, 746.
5. Cypriak, M.; Gupta, Y.; Matyjaszewski, K. *J. Am. Chem. Soc.*, 1991, 113, 1046.
6. Matyjaszewski, K., *Makromol. Chem. Macromol. Symp.* 1991, 42/43, 269.
7. Foucher, D. A.; Tang, B. Z.; Manners, I. *J. Am. Chem. Soc.* 1992, 114, 6246.
8. Manners, I. *Adv. Organomet. Chem.* 1995, 37, in press and references cited therein.
9. a) Low molecular weight polymers ($M_w = 3,500$) consisting of ferrocene and hexasilane units have been recently prepared by the polycondensation reaction of dilithioferrocene.tmeda with 1,6-dichlorohexasilane. Tanaka, M.; Truyuki, H. *Bull. Chem. Soc. Jpn.* 1993, 66, 334.
b) Polysilanes with low loadings of ferrocenyl side groups have been previously reported using Wurtz coupling procedures: see Pannell, K.; Rozell, J.M.; Zeigler, J.M. *Macromolecules* 1988, 21, 278.
10. Foucher, D. A.; Ziembinski, R.; Tang, B. Z.; Macdonald, P. M.; Massey, J.; Jaeger, C. R.; Vansco, G.; Manners, I. *Macromolecules* 1993, 26, 2878.
11. Maxka, J.; Miner, F. K.; Powell, D. R.; West, R. *Organometallics* 1991, 10, 660.

12. We assign the ^{29}Si NMR resonances at - 17.3 and - 6.6 ppm to $\dots\text{FcSiMe}_2\text{FcSiMe}_2(\text{SiMe}_2)_4\dots$ and $\dots\text{FcSiMe}_2\text{FcSiMe}_2(\text{SiMe}_2)_4\dots$ environments, respectively ($\text{Fc} = \text{Fe}(\eta\text{-C}_5\text{H}_4)_2$).
13. Potentials are quoted relative to the ferrocene/ferricenium couple at $E_{1/2} = 0.00$. Polymer solutions were 1×10^{-3} M in CH_2Cl_2 with 0.1 M $[\text{Bu}_4\text{N}][\text{PF}_6]$ as a supporting electrolyte. The working electrode was Pt and the reference electrode was a sce.
14. Diaz, A.; Miller, R.D. *J. Electrochem. Soc.* **1985**, *132*, 834.

Table 1. Thermal Copolymerization Experiments involving 1 and 3

	3 : 1	M_n (PDI)	M_n (PDI)^a	λ_{max}(nm)	T_g(°C)^b
	mol : mol			(polysilane)	
2	0 : 1	250,000 (1.6)	230,000 (1.9)	-	33
5a	1 : 2.2	89,000 (3.5)	1,730 (1.4)	325	69
5b	1 : 1	75,000 (3.1)	1,410 (1.2)	330	-
5c	2 : 1	67,000 (2.4)	1,050 (1.4)	333	-
4	1 : 0	91,000 (3.0)	-	338	-

a) M_n of the remaining oligoferrocenylsilane segments after irradiation with UV light (340 nm) in THF for 18 h.

b) Determined by DSC.

Figure 1 ^{29}Si NMR Spectra of 5a and 5c in the Ferrocenylsilane Region

